

MARKERBOND™ 1587

An amorphous hot melt adhesive developed for raised pavement marker applications. This product remains tough even in elevated temperatures with good low temperature flexibility.

July 10, 2006

Application Temperature	325° F – 380° F
Viscosity at 350° F	3000 – 5000 cP
Heat Stability at 350° F	Excellent at 96 hours
Product Form	¼" pellets in 25 lb boxes
Packaged & Shipped	25 lb corrugated boxes palletized and shrink wrapped at 54 boxes per pallet for a total of 1350 lbs.
Shelf Life	3+ years